

## Acrylic Copolymer Membranes



Acrylic copolymer membranes are our most robust materials for general filtration applications. These are designed to be used as single-use membranes in applications requiring retention properties combined with high tensile strengths. They are ideal for prefiltration, when filtering viscous and difficult-to-filter solutions.



These membranes provide excellent throughput with high liquid flow rates at low differential pressures ensuring robust performance in the most aggressive applications.



The acrylic copolymer membranes are cast on a non-woven nylon support providing excellent durability and handling features which minimize material scrap in device manufacturing. Handled either wet or dry, these membranes are strong and flexible. Our acrylic copolymer membranes comply with United States Pharmacopeia (USP) Biological Reactivity Test, *In Vivo* <88> for biosafety and are non-cytotoxic. In addition, these membranes withstand gamma, UV, and ETO sterilization providing compatibility to your most stringent sterilization requirements and medical applications.

### Applications

- General filtration
- Protects final filters (prefilter)

### Sealing

- Mechanical
- Heat
- Ultrasonic
- Insert molding
- RF welding
- Adhesive

## Product Information

### Specification

Hydrophilic Supported Acrylic Copolymer

Typical Membrane Characteristics

Base Material	Nominal Pore Size (μm)	Thickness	
		mils	μm
Acrylic copolymer on non-woven nylon support	0.2	6.0-12.0	152.4-304.8
	0.45	6.0-12.0	152.4-304.8
	0.8	6.0-12.0	152.4-304.8
	1.2	6.0-12.0	152.4-304.8
	3.0	4.5-8.5	114.3-215.9
	5.0	4.5-8.5	114.3-215.9

Wet time: ≤ 15 seconds

Typical Performance Characteristics

Water Bubble Point		Water Flow (mL/min/cm <sup>2</sup> @ 0.7 bar, 10 psi)
psi	bar	
≥ 25.0	≥ 1.72	≥ 10.6
≥ 16.0	≥ 1.10	≥ 21.0
≥ 8.0	≥ 0.55	≥ 88.0
≥ 6.0	≥ 0.41	≥ 176.0
≥ 3.0	≥ 0.21	≥ 378.0
≥ 2.0	≥ 0.14	≥ 662.0

## Ordering Information

Custom roll, sheet, and disc sizes available upon request.

Please contact your local sales representative for additional information.

Part Number	Description	Pkg
<b>S80158</b>	Versapor-200 W/WA membrane, 0.2 μm, 8" x 10" sheet	1/pkg
<b>S80104</b>	Versapor-450 W/WA membrane, 0.45 μm, 8" x 10" sheet	1/pkg
<b>S80105</b>	Versapor-800 W/WA membrane, 0.8 μm, 8" x 10" sheet	1/pkg
<b>S80143</b>	Versapor-1200 W/WA membrane, 1.2 μm, 8" x 10" sheet	1/pkg
<b>S80151</b>	Versapor-3000TN W/WA membrane, 3.0 μm, 8" x 10" sheet	1/pkg
<b>S80191</b>	Versapor-5000TN W/WA membrane, 5.0 μm, 8" x 10" sheet	1/pkg



PALL CORPORATION

#### Corporate Headquarters

Port Washington, NY, USA

#### European Headquarters

Fribourg, Switzerland

#### Asia-Pacific Headquarters

Singapore

Visit us on the Web at [www.pall.com/medical](http://www.pall.com/medical)  
Contact us at [www.pall.com/contact](http://www.pall.com/contact)

Pall Corporation has offices and plants throughout the world. To locate the Pall office or distributor nearest you, visit [www.pall.com/contact](http://www.pall.com/contact).

The information provided in this literature was reviewed for accuracy at the time of publication. Product data may be subject to change without notice. For current information consult your local Pall distributor or contact Pall directly.

© Copyright 2022, Pall Corporation. Pall, , and Versapor are trademarks of Pall Corporation. ® Indicates a trademark registered in the USA.

Z20607.12OGL  
05/2022